



Aalborg Universitet

AALBORG UNIVERSITY
DENMARK

Implications for the Structural Origin of the Increase in Configurational Heat Capacity with Increasing B₂O₃ Content in Borosilicate Glasses

Liu, Hao; Smedskjær, Morten Mattrup; Tao, Haizheng; Zhao, Xiujian; Yue, Yuanzheng

Published in:
International Commission on Glass (ICG) Annual Meeting

Publication date:
2015

Document Version
Publisher's PDF, also known as Version of record

[Link to publication from Aalborg University](#)

Citation for published version (APA):
Liu, H., Smedskjær, M. M., Tao, H., Zhao, X., & Yue, Y. (2015). Implications for the Structural Origin of the Increase in Configurational Heat Capacity with Increasing B₂O₃ Content in Borosilicate Glasses. In *International Commission on Glass (ICG) Annual Meeting*

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal -

Take down policy

If you believe that this document breaches copyright please contact us at vbn@aub.aau.dk providing details, and we will remove access to the work immediately and investigate your claim.

Implications for the Structural Origin of the Increase in Configurational Heat Capacity with Increasing B₂O₃ Content in Borosilicate Glasses

Hao Liu^{a,b*}, Morten M. Smedskjaer^b, Haizheng Tao^a, Xiujuan Zhao^a, Yuanzheng Yue^{a,b}

^aState Key Laboratory of Silicate Materials for Architectures, Wuhan University of Technology, Wuhan 430070, PR China

^bSection of Chemistry, Aalborg University, DK-9220 Aalborg, Denmark

*E-mail address of presenting author: hal@bio.aau.dk

Keywords: Borosilicate glasses; Intermediate range structure; Glass transition; Configurational heat capacity

In this work, we explore the structural origin of the compositional evolution of the jump in isobaric heat capacity (ΔC_p) during the glass transition in a series of $(75q)\text{B}_2\text{O}_3$ -($75(1-q)$) SiO_2 -15 Na_2O -10 CaO glasses. ΔC_p represents the difference between the liquid C_{pl} and the glass C_{pg} and is usually approximated as the configurational heat capacity ($C_{p,\text{conf}}$), particularly for relative strong inorganic system. As determined by differential scanning calorimetry (DSC), ΔC_p is found to increase non-linearly when substituting B_2O_3 for SiO_2 . By using Raman spectroscopy we investigate whether and how the increase in ΔC_p is associated with changes in glass structure, particularly in the intermediate range order (IRO) structure. Raman bands in the medium-frequency region of 550-810 cm^{-1} can be assigned to the vibrational modes of various superstructural units, reflecting the IRO. Our results demonstrate a possible link between the evolution of IRO structures and ΔC_p , which reflects the number of minima in a multidimensional potential energy surface. In the silica-rich compositions, two types of borosilicate units exist, leading to the rapid increase of ΔC_p with B_2O_3 content. In the compositions with similar concentration of B_2O_3 and SiO_2 , the concentration of borosilicate units and borate superstructures change in an opposite way, leading to an approximate constant value of ΔC_p as a function of composition. In the boron-rich compositions, the presence of six-membered borate rings with one and two $[\text{BO}_{4/2}]^-$ groups are responsible for the increase of ΔC_p with B_2O_3 content.